

## LD2

### Technical Specifications

| Properties   | ANSI A208.2-2016 (Grade LD2)                   |                              |
|--|--|------------------------------|
|  | Metric   | Imperial                     |
| Moisture content   | Max. 10%                                       |                              |
| Density range  | 500–550 kg/m <sup>3</sup>                      | 31.2–34.3 lb/ft <sup>3</sup> |
|  | Typical density value for Uniboard mills       |                              |
| Thickness tolerance:   |  |                              |
| Between panels   | +0.125 mm to –0.375 mm                         | +0.005 in to –0.015 in       |
| Within panels  | ± 0.125 mm                                     | ± 0.005 in                   |
| Modulus of rupture   | 2.8 N/mm <sup>2</sup>                          | 406 psi                      |
| Modulus of elasticity  | 500 N/mm <sup>2</sup>                          | 72,500 psi                   |
| Internal bond  | 0.14 N/mm <sup>2</sup>                         | 20 psi                       |
| Linear expansion   | < 0.40%  |                              |
| Screw holding:   |  |                              |
| Face   | 520 N  | 117 lb                       |
| Core   | n/a  | n/a                          |
| Formaldehyde emission  | TSCA Title VI; ULEF is available upon request. |                              |
| Length-Width   | ± 2.0 mm                                       | ± 0.08 in                    |
| Uniboard Door Core meets the requirements of ANSI A208.2-2016/Grade LD2 and is available as FSC® certified |  |                              |
| Uniboard Door Core meets CARB Phase 2 standards  |  |                              |

Although the information in this document is presented in good faith and believed to be correct, Uniboard makes no representations or warranties as to the completeness or accuracy of the information. Uniboard shall have no liability for any errors or omissions contained therein or for any consequences of same.